

Preliminary Product Information Sheet

Microanalytical Reference Material

OREAS-600*-NP

Nano-particulate pressed powder pellet

Assigned Values

Analyte	Value	Uncertainty (95% CL)	Unit
Li	18.7	0.7	µg/g
Be	1.69	0.08	µg/g
Na	0.587	0.013	g/100g
Mg	0.772	0.016	g/100g
Al	6.78	0.12	g/100g
P	0.060	0.001	g/100g
K	1.80	0.03	g/100g
Ca	1.88	0.03	g/100g
Sc	5.95	0.11	µg/g
Ti	0.242	0.007	g/100g
V	45.4	1.0	µg/g
Cr	27.5	2.0	µg/g
Mn	0.071	0.002	g/100g
Fe	2.38	0.05	g/100g
Co	7.06	0.41	µg/g
Ni	16.5	1.2	µg/g
Cu	482	10	µg/g
Zn	615	11	µg/g
Ga	18.7	0.7	µg/g
As	89	4	µg/g
Se	6.97	0.98	µg/g
Rb	75	4	µg/g
Sr	186	4	µg/g
Y	9.93	0.29	µg/g
Zr	94	2	µg/g
Nb	7.98	0.31	µg/g
Mo	2.20	0.21	µg/g
Ag	24.8	0.4	µg/g

Assigned Values

Analyte	Value	Uncertainty (95% CL)	Unit
Cd	3.37	0.14	µg/g
In	0.75	0.05	µg/g
Sn	2.12	0.16	µg/g
Sb	14.3	0.7	µg/g
Te	7.34	0.43	µg/g
Cs	9.42	0.45	µg/g
La	23.0	1.4	µg/g
Ce	47.7	1.4	µg/g
Pr	5.42	0.45	µg/g
Nd	19.5	1.0	µg/g
Sm	3.56	0.23	µg/g
Eu	1.03	0.20	µg/g
Gd	3.12	0.50	µg/g
Tb	0.40	0.05	µg/g
Dy	2.05	0.12	µg/g
Ho	0.36	0.03	µg/g
Er	0.97	0.09	µg/g
Yb	0.91	0.05	µg/g
Lu	0.13	0.01	µg/g
Hf	2.90	0.09	µg/g
Ta	0.63	0.11	µg/g
W	4.20	0.49	µg/g
Au	0.200	0.002	µg/g
Tl	1.11	0.03	µg/g
Pb	193	6	µg/g
Bi	6.39	0.34	µg/g
Th	9.38	0.42	µg/g
U	2.69	0.11	µg/g

*The original manufacturer (OREAS) is not liable for any issues occurring from the use of this material since they took no part in the manufacturing of the pellets.

The assigned values are the present best estimates of the true content for each element in the original powder. They are based on the certified values given for the four acid digestion for full suite ICP-OES and ICP-MS in the original certificate of analysis.

Please note that four acid digestion is a nearly full dissolution, which is capable of dissolving most minerals, but not all.

Gold (Au) is based on values characterised via fire assay with AAS, ICP-OES and gravimetric finish.

The uncertainty is based on the method specific 95 % confidence interval given in the original certificate.

Detailed information and background data can be found in the original certificate of analysis and corresponding data package issued by OREAS.

Pellet serial number: {SERIENNUMMER}

Manufactured for: {METHODE}

Size: {GROESSE}

Date of dispatch: {LIEFERDATUM}

Intended Use

This microanalytical reference material (MRM) is designed for use by laboratories undertaking the determination of major and trace element mass fractions in Au-Ag-Cu ore blended with Rhyodacite and equivalent matrices with LA-ICP-MS (Laser Ablation Inductively Coupled Plasma Mass Spectrometry), μ XRF/XRF (Micro X-ray Fluorescence Spectroscopy) and LIBS (Laser-Induced Breakdown Spectroscopy). It is suitable for calibration and as a secondary reference material for the assessment of a measurement procedure and quality control. Note that the material may only be used for a single purpose in the same measurement process. For example, it must not be used for calibration and method validation at the same time.

Description of the MRM

This MRM is a nanoparticulate pressed powder pellet of the Au-Ag-Cu ore blended with Rhyodacite powder "OREAS-600". The original powder, purchased from the Ore Research & Exploration Pty. Ltd. (OREAS), was subjected to our own material-specific milling protocol, and pressed without any binders using a programmable hydraulic press. The fortification of contrasting colour surrounding the reference material is, according to the manufacturer, an "organic compound". The exact composition is not specified any closer. The certificate of analysis is available on demand.

Handling advice and Storage

Avoid touching the pellet's surface directly in order to prevent contamination. Also, do not clean the surface with any liquids as it may compromise the pellet's integrity.

Please note the label marks the bottom of the pellet.

If using a pressed pellet not ordered specifically for μ XRF and or XRF please consider the sample thickness.

Store the MRM in a desiccator and or in a dark and dry environment.

The myStandards GmbH cannot be held responsible for changes that happen during storage of the material at the customer's premises, especially with respect to opened samples.

Period of Validity

Provided the storage and handling conditions are met, no chemical alteration is known to exist, and the assigned values will remain stable. Therefore, the product information and assigned values for this MRM are valid for one year from the date of dispatch. This validity may be extended as further evidence of stability becomes available. The manufacturer will inform the customer if any alterations occur.

Safety instructions

Nano-particulate powders can cause harm if ingested, inhaled or in contact with skin. In their pressed form however, they do not exhibit any dusting. If a pellet should accidentally break, we advise wearing a dust mask during clean up.

Further Information

This MRM has been produced in accordance with the recommendations specified in ISO Guides 30 to 35. Due to processing a part of the sample material may be seen on the fortification, this does not reduce the performance of the MRM. Please refrain from using this part of the pellet.

The pellets are sold exclusively via the myStandards GmbH and authorised subcontractors.

Document History

Version	Date	Changes applied
1.0	05.12.2022	First publication
1.1	08.12.2022	Adaptation and extension of the description of the assigned values
2.0	04.04.2023	Adaptation to automatically fill in the date and individual pellet characteristics

References

Hamlyn C., *CERTIFICATE OF ANALYSIS FOR HIGH SULPHIDATION EPITHERMAL Ag-Cu-Au ORE CERTIFIED REFERENCE MATERIAL OREAS 600*, Certificate of Analysis: COA-1063-OREAS600 Revision 1, 16th November, 2016, Ore Research & Exploration Pty. Ltd., 2016, available online at www.oreas.com

OREAS 600 DataPack.xlsx, Ore Research & Exploration Pty. Ltd., retrieved on 13.10.2022 from www.oreas.com/crm/oreas-600/

Legal notice

Our order, sales and delivery conditions apply. The valid version of our general terms and conditions (status 01.09.2019) - can be found on our website: <https://www.my-standards.com/terms-and-conditions/>. They are also available on request.